

VERSION WITH MARKINGS TO SHOW CHANGES MADESPECIFICATION:

Specification at page 2, line 7:

Hence, regarding an unnecessary halogen-containing flame-retardant resin composition, techniques of detoxification have been developed. As disclosed in Japanese Patent Application Laid-Open No. 2000 - 117738, it is common to thermally decompose resin and remove and recover it in the forms of halogenated low molecular weight compounds and treatment is generally carried out at a high temperature, at 300°C or higher. Also, as disclosed in Japanese Patent Application Laid-Open No. 2000 - 44966, the resin is hydrogenated and decomposed in the presence of a catalyst to remove and recover it in the forms of halogenated low molecular weight compounds. The treatment temperature is also high, 300 to 420°C, as in the case of the thermal decomposition. However, in these cases, since the resin is thermally decomposed or hydrogenated and decomposed, although an oil or a gas can be recovered to be reused, it cannot be reused as resin. Besides that, dioxins are probably produced by heating at the time of the treatment.

RECEIVED
APR 23 2002
TC 1700